

Artshield™ Mattex UV

Overlaminating Film

Artshield™ Mattex UV 75µ (3 mil) is a 50µ (2 mil) UV stabilized, pre-perforated clear PVC overlaminating film with a semi-matte finish, coated on one side with a heat activated solvent acrylic adhesive, which is protected by a bleached Kraft grey grid release paper coated on one side with siliconized polyethylene. Available in various sizes.

Typical Applications

- Ideal for laminating canvas-mounted photographs.
- When provided with adequate dwell time, temperature and pressure, the laminating film will take on the texture of the canvas for an authentic textured finish.

Product Structure

Film	Satin-Matte PVC	75µ (3 mil)
Adhesive	Solvent Acrylic (Heat Activated)	
Release Liner	1 Side PE Coated Bleached Kraft Grey Grid Paper (Moisture Stable)	

Physical Characteristics

Film Thickness	50µ (2 mil)
Adhesive Layer	25µ (1 mil)
Ratio Film/Adhesive	2:1
UV Protection Factor	Film contains UV stabilizers, which prevent film degradation and provide UV protection to the underlying image
Outdoor Durability	3 years
Heat Resistance Range	70°C - 95°C (158°F - 203°F)
Peel Strength (20 min, FTM1)	18 N/25mm

Process Settings

Equipment Type	Temperature	Dwell Time
Roller Laminator	Not recommended	
Press	85°C to 99°C (185°F to 210°F)	2 to 6 minutes

IMPORTANT NOTE:

Information is intended only as a guide and is given without guarantees. Purchasers should independently determine, prior to use, the suitability of each material for their specific purpose. Follow the indications on the package, ask for the safety data sheets and always follow the indications contained therein.

Only the correct use of the product will allow satisfactory results. For this reason, Drytac is not responsible for improper use of the product, either by application or substrate applied to. Make certain that product is right for the desired use, and work according to the instructions given in our technical data sheets. If in doubt of the appropriate application methods or use, contact Drytac at one of the phone numbers listed below.